



StandardTolerance_table Rotational- molding_Roto-cast

	Typical	Feasible
Materials:	Plastic HDPE Nylon 11 Nylon 12 LLDPE Cross-Linked PE	
Standard tolerance:	± 2%	± 0.5%
Wall thickness:	1/4 to 3/8 in	

Note that the values represent normal production practice at the most economical level. Greater accuracy should only be specified where required to avoid additional prices. Disclaimer: All tolerance specifications reflect the approximate range of a process's capabilities and should be viewed only as a guide. Actual capabilities are dependent upon manufacturing, equipment, material, and part requirements.